NATURAL RESISTANCE TO MARINE BORERS OF NINE NORTH AND NORTH-EASTERN BRAZILIAN WOOD SPECIES*

Fernando da Gama Serpa**

Peter Karstedt***

RESUMO

Durante 2 anos, 9 espécies nativas brasileiras foram expostas ao ataque de daninhos marinhos no porto de Recife/PE, para testar sua resistência natural. Paralelamente realizava-se análises da água no local da pesquisa, assim como em laboratório para verificar o teor de SiO_2 e de alcalóide das madeiras.

A madeira de Eschweillera luschnathii comprovou ser a mais resistente, apresentando após dois anos, apenas leves ataques na superfície. Bastante resistente foram também as espécies Manilkara longifolia e Goupia glabra.

O maior teor de SiO_2 foi constatado na Eschweillera luschnathii. Na espécie Diplotropis purpurea foi constatada a presença de SiO_2 e alcalóide. Mas assim mesmo esta espécie apresentou apenas resistência média.

As análises da água do porto tornaram evidente que de acordo com o aumento do teor de SiO_2 diminui o teor de sal.

Como daninhos foram identificados a Bankia fimbriatula e Martesia striata.

1. INTRODUCTION

This article evaluates the natural resistance of eight north and northeastern brazilian and one south brazilian wood species to marine borers. The goals of the present study were:

a) to get acquainted with the reaction of national wood species to marine enemies,

b) to establish a method with which to measure the resistance of wood against xilophages in a natural water environment and,

c) to test a method of examining the intensity of attack by x-raying the samples.

2. MATERIAL AND METHODS

The following species were tested: *Araucaria angustifolia* (Bert.) O. Ktze. (Pinho do Paraná), *Copaifera langsdorffii* Desf. (Pau d'óleo), *Diplotropis purpurea* (Rich.) Amsh. (Sucupira parda), *Eschweillera luschnathii* Miers (Imbiriba), *Goupia glabra* Aubl. (Cupiuba), *Manilkara longifolia* (A.DC.) Dub. (Maçaranduba), *Peltogyne confertiflora* (Hayne) Benth. (Pau roxo), *Tabebuia*

avellanadae Lorentz ex Griseb. (Pau d'arco) and *Virola gardneri* (DC.) Warb. (Urucuba). The studies were made in the estuary of the river Capibaribe in the port of Recife from december 1975 until december 1977. They were made according to a method devised by the National Laboratory for Civil Engineering in Lisbon. Ten (10) samples of each species measuring 5cm x 5 cm x 15cm were used. A frame with the samples was immersed in 1,5m of water so that during low tide the samples were above the water (Photo 1). Every six months the samples were examined.

Analysis of the SiO_2 and alcaloid content of the wood samples were made in the laboratory and the silica — and salinity values of the por water were also analysed. The grade of attack by xilophages was checked by x-raying the wood samples.

3. RESULTS AND CONCLUSIONS

After 12 months 8 species were attacked. Only the samples of *Eschweillera luschnathii* still were resistant to the attack by marine borers. (Photo 3 and Table 1). After 18 months this species also

* Paper presented at the IUFRO-Meeting in Xalapa, Vera Cruz, México, on July 18-21, 1978, on Actual Trends of the Wood Preservation Research in Tropical America. Subject Group S.5.03 Wood Protection.

** Head of the Division of Timber and Fibers, Technological Institute of the State of Pernambuco, Recife, Brazil.

*** Professor of Wood Technology and Wood Preservation, Federal University of Paraná, Brazil.

showed slight signs of superficial damage and after 24 months immersion the transversal surface showed signs of attack. Apart from *Eschweilera luschnathii* the only other species showing limited signs of attack were *Manilkara longifolia* and *Goupia glabra*. (Photo 4 and Table 1). The resistance of other brazilian wood species of the genus *Eschweilera* has already been mentioned in the literature (FOUGEROUSSE, 1971). Adding *E. luschnathii* to the list confirms that this genus includes several species with high resistance to marine xilophagues.

Xilophagues of the species *Bankia fimbriatula* Roch & Moll (Teredinidae) and *Martesia striata* L. (Pholadidae) and two further, as yet not identified species, were found in the wood samples. There was no literature found mentioning the identified species as occurring along the brazilian coast. A relation between wood resistance to marine borers and the SiO_2 content of the wood was evident with a greater resistance occurring in those species with a higher SiO_2 — content. (Table 2). But it was not possible to determine how high the content of SiO_2 has to be to exclude damage. The highest SiO_2 content was found in *Eschweilera luschnathii* which had 0,266%. *Diploporis purpurea* was the only species that also had alcaloid-content. Nonetheless this species had average attack after 2 years. (Table 1).

The results of the water analysis during the research period showed no apparent annual cycle in the silica or salinity values. (Figure 1). It was found that with an increasing silica-content of the water the salt content decreased.

It was not possible to observe how this affected the intensity of the xilophagues attack, but future research will be concentrated on this fact.

4 SUMMARY

During 2 years 9 brazilian wood species were exposed to attack by marine borers in the harbour of Recife, Pernambuco to test their natural resistance. At the same time the port water at the site was examined and laboratory analysis of the SiO_2 and alcaloid content in the wood were made.

The highest level of resistance was found in the species *Eschweilera luschnathii* which only showed slight superficial attack after 2 years. The species *Manilkara longifolia* and *Goupia glabra* were fairly resistant.

Eschweilera luschnathii also had the highest SiO_2 content. In *Diploporis purpurea* SiO_2 and alcaloid were found. Nonetheless this species only showed average resistance. The water analysis showed that with increasing silica-content the salinity decreased.

Bankia fimbriatula and *Martesia striata* were identified as the damaging xilophagues.

5. LITERATURE

1. FOUGEROUSSE, M. & CUENEAU, P. — further research on X-ray examination of wood panels exposed to Teredinidae. The Journal of the Institut of Wood Scienc, 5 (6): 3-12, dec. 1971.
2. FOUGEROUSSE, M. & LUCAS, S. — Emploi de la radiographie dans les recherches sur la pathologie et la préservation du bois en milieu marin. Centre Technique Forestiers Tropical. (s.n.t.).
3. FRANCO, E. J. S. — Sur l'aptitude de quelques bois africains a l'emploi dans les travaux maritimes et la construction navale. *Memória*, nº 243, 1965. 17 p.
4. PORTUGAL. LABORATORIO NACIONAL DE ENGENHARIA CIVIL. Resistência natural de madeiras tropicais aos xilófagos marinhos. Lisboa, 1968. 14 p.
5. TAVARES, S.; TAVARES, E. J. de S. & SERPA, F. G. — Ataque de xilófagos marinhos em estacas de madeiras utilizadas na construção da parte rodo-ferroviária do porto de Recife. *B. Téc., Viação e Obras Públicas de Pernambuco*, 96 (1): 49-52, 1971.
6. FOUGEROUSSE, M. — Natural resistance of tropical timbers to attack by marine wood-destroying organism. in: *Marine borers, fungi and fouling organisms of wood*, O.E.C.D. 1971, Chapter 17. Centre Technique Forestier Tropical.

QUADRO 1 — RESISTÊNCIA DAS MADEIRAS SUBMERSAS NO ESTUÁRIO DO RIO CAPIBARIBE NO PORTO DE RECIFE

(TABLE 1) — Natural resistance of the wood species submerged at the banks of the river Capibaribe in the harbour of Recife)

NOME LATINO (Latin name)	NOME VULGAR (Local name)	12 MESES (12 months)	24 meses (24 months)
<i>Araucaria angustifolia</i>	Pinho do Paraná	destruída	destruída
<i>Copaifera langsdorffii</i>	Pau d'óleo	muito atacada	destruída
<i>Diploptropis purpurea</i>	Sucupira parda	pouco atacada	medianamente atacada
<i>Eschweilera luschnathii</i>	Imbiriba	sem ataque	medianamente atacada
<i>Goupia glabra</i>	Cupiuba	pouco atacada	pouco atacada
<i>Manilkara longifolia</i>	Maçaranduba	pouco atacada	pouco atacada
<i>Peltogyne confertiflora</i>	Pau roxo	medianamente atacada	pouco atacada
<i>Tabebuia avellanedae</i>	Pau d'arco	medianamente atacada	medianamente atacada
<i>Virola gardneri</i>	Urucuba	muito atacada	destruída

Pouco atacada = (little attack) = até 10% da superfície útil atacada

medianamente atacada = (medium attack) = até 40% da superfície útil atacada

muito atacada = (severe attack) = até 75% da superfície útil atacada

destruída = (destroyed) = mais do que 75% da superfície útil atacada

QUADRO 2 — VALORES DE SILÍCIA NAS MADEIRAS ESTUDADAS (%)

(TABLE 2) — (Contents of SiO₂ in the tested wood species)

ESPÉCIE (Specie)	NOME VULGAR (local name)	SiO ₂
<i>Copaifera langsdorffii</i> (Desf.)	Pau d'óleo	0,004
<i>Manilkara longifolia</i> (A.DC.) Dub.	Maçaranduba	0,006
<i>Virola gardneri</i> (DC.) Warb.	Urucuba	0,007
<i>Araucaria angustifolia</i> (Bert.) O. Ktze.	Pinho do Paraná	0,008
<i>Tabebuia avellanedae</i> Lorentz ex Griseb	Pau d'arco	0,010
<i>Diploptropis purpurea</i> (Rich.) Amsh.	Sucupira parda	0,012
<i>Goupia glabra</i> Aubl.	Cupiuba	0,018
<i>Peltogyne confertiflora</i> (Hayne)	Pau roxo	0,019
<i>Eschweilera luschnathii</i> Miers.	Imbiriba	0,266

OBS.: % SiO₂ em madeira com 0% de teor de umidade

(% SiO₂ in timber with 0% water contents)

Figura 1 — Variação da temperatura, salinidade e conteúdo de Silica na água durante o período de observação.

(Figure 1): (Variation of temperature, salinity and contents of silica in the water during the period of observation)

FOTO 1

Moldura com os corpos de prova no estuário do Rio Capibaribe no porto de Recife.
(The frame with the test samples located at the bank of the river Capibaribe, in the the port of Recife)

FOTO 2

Secção de estaca de “Eschweilera luschnathii” (Imbiriba) após 18 meses de imersão utilizada na construção da ponte rodo-ferroviária no porto de Recife.

(Section of a bridge pole form “Eschweilera luschnathii” after 18 months of submersion in the port of Recife).

FOTO 3

**Corpos de prova das madeiras após 12 meses de imersão.
(Testsamples after 12 month of submersion).**

FOTO 4

**Corpos de prova das madeiras após 24 meses de imersão.
(Testsamples after 24 months of submersion).**